

DIO DESK

Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range			Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+10.00	to	-11.00	0.75~2.50	0.5,1,2,4,5,6,7,8,9,10,12	75	15	OFC
1.60	1.597	1.30	42	400	Clear	S+9.50	to	-11.00	0.75~2.50	0.5,1,2,4,5,6,7,8,9,10,25,12	75	15	OFM
1.67	1.665	1.35	32	400	Clear	S+11.50	to	-11.00	0.75~2.50	0.5,1,2,4,5,6,7,8,9,10,11,13	75	15	OFH
1.74	1.738	1.47	31	390	Clear	S+10.50	to	-12.00	0.75~2.50	0.5,1.5,3.5,5,6,7.5,8.5,10,25,12.5	75	15	OFU
TVX	1.530	1.11	45	400	Clear	S+7.00	to	-10.50	0.75~2.50	0.5,1,2,2.5,3,4,5,6,7,8	75	15	OFV
Tribrid	1.607	1.22	41	400	Clear	S+9.50	to	-11.00	0.75~2.50	1,2.5,4,5,6,7,8,9,10,11	75	15	OF3
Polycarbonate	1.586	1.17	31	380	Clear		to		0.75~2.50		75	15	OFFP
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to	-11.00	0.75~2.50	2.25,4.25,5.25,6.25,8.25	76	15	OFA
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+9.50	to	-11.00	0.75~2.50	0.5,1,2.5,4,5,6,7,8,9,10,11	75	15	OFB
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+7.50	to	-9.00	0.75~2.50	2.25,4.25,6.25,8.25	76	15	OFF
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+7.00	to	-11.00	0.75~2.50	0.5,2,4,5,6,8	70	15	OFS
SunAct 1.6	1.597	1.64	42		Grey/Brown		to		0.75~2.50	6,8	75	15	OFO

* The true base curve will be selected by an Index of material