

DIO FATIFREE

Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range		Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+10.00	to -11.50	0.50	0.5,1,2,4,5,6,7,8,9,10,12	75	-	
1.60	1.597	1.30	42	400	Clear	S+10.00	to -12.00	0.50	0.5,1,2,4,5,6,7,8,9,10,25,12	75	-	
1.67	1.665	1.35	32	400	Clear	S+11.50	to -12.00	0.50	0.5,1,2,4,5,6,7,8,9,10,11,13	75	-	
1.74	1.738	1.47	31	390	Clear	S+10.50	to -13.00	0.50	0.5,1.5,3.5,5,6.75,8.5,10.25,12.5	75	-	
TVX	1.530	1.11	45	400	Clear	S+7.00	to -11.00	0.50	0.5,1,2,2.5,3,4,5,6,7,8	75	-	
Tribrid	1.607	1.22	41	400	Clear	S+9.50	to -11.00	0.50	1,2.5,4,5,6,7,8,9,10,11	75	-	
Polycarbonate	1.586	1.17	31	380	Clear		to	0.50		75	-	
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to -11.50	0.50	2.25,4.25,5.25,6.25,8.25	76	-	
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+10.00	to -11.00	0.50	0.5,1,2.5,4,5,6,7,8,9,10,11	75	-	
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+7.50	to -10.00	0.50	2.25,4.25,6.25,8.25	76	-	
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+7.00	to -12.00	0.50	0.5,2,4,5,6,8	70	-	
SunAct 1.6	1.597	1.64	42		Grey/Brown		to	0.50	6,8	75	-	

* The true base curve will be selected by an Index of material