

DIO SPORTS OPTIMA

Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range			Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+6.00	to	-4.25	0.75~3.50	6/8	80	16/18/20/22	DXC
1.60	1.597	1.30	42	400	Clear	S+6.00	to	-4.25	0.75~3.50	6/8	80	16/18/20/22	DXM
1.67	1.665	1.35	32	400	Clear	S+6.00	to	-4.25	0.75~3.50	6/8	80	16/18/20/22	DXH
Polycarbonate	1.586	1.17	31	380	Clear		to		0.75~3.50	6/8	75	16/18/20/22	DXP
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+6.25	to	-5.50	0.75~3.50	6/8	76	16/18/20/22	DXA
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+5.25	to	-4.50	0.75~3.50	6/8	75	16/18/20/22	DXB
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+4.50	to	-5.25	0.75~3.50	6/8	76	16/18/20/22	DXF
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+5.00	to	-3.50	0.75~3.50	8	70	16/18/20/22	DXS
SunAct 1.6	1.597	1.64	42		Grey/Brown		to		0.75~3.50	6/8	75	16/18/20/22	DXO
Polarized 1.5	1.498	1.32	58	350	Grey/Brown	S+4.50	to	-4.00	0.75~3.50	6/8	75	16/18/20/22	DXD
Polarized 1.6	1.594	1.30	42	400	Grey/Brown	S+4.75	to	-2.50	0.75~3.50	8	75	16/18/20/22	DXE
NXT Sun	1.530	1.11	45	400	Grey/Brown/etc	S+5.00	to	-5.00	0.75~3.50	6/8	80	16/18/20/22	DXN
NXT Polar	1.530	1.11	45	400	Grey/Brown	S+5.00	to	-5.00	0.75~3.50	6/8	75	16/18/20/22	DXN
NXT Varia	1.530	1.11	45	380	Grey/Brown/etc	S+5.00	to	-5.00	0.75~3.50	6/8	80	16/18/20/22	DXN
NXT Varia Polar	1.530	1.11	45	400	Grey	S+5.00	to	-5.00	0.75~3.50	6/8	75	16/18/20/22	DXN

* The true base curve will be selected by an Index of material