

# DIO TAB

## Product Specifications

Material	Refractive Index	Gravity	Abbe value	UV cut off (mm)	color	Power Range		Add	Nominal Base Curve	Effective Max DIA	Fitting Height	ID mark
1.50	1.498	1.32	58	350	Clear	S+11.25	to -11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,12	75	16/18/20	TAC
1.60	1.597	1.30	42	400	Clear	S+10.00	to -11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,25,12	75	16/18/20	TAM
1.67	1.665	1.35	32	400	Clear	S+11.50	to -11.00	0.75~3.50	0.5,1,2,4,5,6,7,8,9,10,11,13	75	16/18/20	TAH
1.74	1.738	1.47	31	390	Clear	S+10.50	to -12.00	0.75~3.50	0.5,1,5,3,5,5,6,7,8,5,10,25,12.5	75	16/18/20	TAU
TVX	1.530	1.11	45	400	Clear	S+7.00	to -10.50	0.75~3.50	0.5,1,2,2,5,3,4,5,6,7,8	75	16/18/20	TAV
Tribrid	1.607	1.22	41	400	Clear	S+9.50	to -11.00	0.75~3.50	1,2,5,4,5,6,7,8,9,10,11	75	16/18/20	TA3
Polycarbonate	1.586	1.17	31	380	Clear		to	0.75~3.50		75	16/18/20	TAP
Transitions 1.5	1.498	1.32	58	350	Grey/Brown	S+7.00	to -11.00	0.75~3.50	2.25,4.25,5.25,6.25,8.25	76	16/18/20	TAA
Transitions 1.6	1.597	1.30	42	400	Grey/Brown	S+9.50	to -11.00	0.75~3.50	0.5,1,2,5,4,5,6,7,8,9,10,11	75	16/18/20	TAB
Transitions TVX	1.530	1.11	45	400	Grey/Brown	S+7.50	to -9.00	0.75~3.50	2.25,4.25,6.25,8.25	76	16/18/20	TAF
Sunsensors	1.555	1.17	38	370	Grey/Brown	S+7.00	to -11.00	0.75~3.50	0.5,2,4,5,6,8	70	16/18/20	TAS
SunAct 1.6	1.597	1.64	42		Grey/Brown		to	0.75~3.50	6,8	75	16/18/20	TAO

\* The true base curve will be selected by an Index of material